

Chemlok® 286 Tacky Tie Cement

Description

LORD Chemlok® 286 tacky tie cement is designed for use over rubber-to-metal adhesives when bonding natural rubber to metal in lining operations. It is composed of a mixture of polymers, organic compounds and mineral fillers dissolved or dispersed in an organic solvent system. Chemlok 286 tie cement is suitable for cure by autoclave, open steam or chemical techniques.

Features and Benefits

Easy to Use – allows the uncured rubber lining to be repositioned without damage to the underlying adhesive film.

High Green Strength – provides quick grab and tenacious green strength for use in sharp radius areas such as flanges.

Versatile – functions well for bonding natural rubber or natural-backed linings; can be used over a variety of adhesive systems such as Chemlok 289/290 adhesive.

Application

Mixing – Thoroughly stir Chemlok 286 tie cement before use, and agitate sufficiently during use to keep dispersed solids uniformly suspended. If dilution is needed, use xylene or toluene as diluents.

Applying – Apply tie cement by brush or roll coat methods to adhesive-coated metal. Recommended dry film thickness of Chemlok 286 tie cement is 12.7 micron (0.5 mil).

Drying/Curing – Allow tie cement to dry to the touch prior to rubber layup. Parts coated with Chemlok 286 tie cement can be stored for up to three days prior to rubber layup without affecting bond performance.

Cleanup – Use xylene, toluene or naphtha solvents for clean up.

Shelf Life/Storage

Shelf life is six months from date of shipment when stored by the recipient in a well ventilated area at 21-27°C (70-80°F) in original, unopened container. Keep container closed when not in use.

Typical Properties*

Appearance	Black Liquid
Viscosity, cps @ 25°C (77°F) Brookfield LVT Spindle 2, 30 rpm	450-1200
Density kg/m ³ (lb/gal)	874.7-898.7 (7.3-7.5)
Solids Content by Weight, %	12-16
Flash Point (Seta), °C (°F)	4 (40)
Solvents	Toluene
Theoretical Coverage, m ² /gal (ft ² /gal) @ 12.7 micron (0.5 mil) dry film thickness	37 (397)

*Data is typical and not to be used for specification purposes.

LORD TECHNICAL DATA

Cautionary Information

Before using this or any LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

Chemlok is a trademark of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide.

LORD Corporation World Headquarters

111 Lord Drive
Cary, NC 27511-7923
USA

Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

www.lord.com

For a listing of our worldwide locations, visit LORD.com.

