

RS-400 Pre Cured Red Natural Rubber High abrasion resistant, engineered for the mining industry. RubberSource Premium cold bonding quality rubber, a soft rubber compound mainly for High wet abrasion resistance applications, specifically engineered for the mining industry. It outlasted the best of market available materials in the mining industry around the world. RubberSource natural rubber has excellent physical properties such as; elongation, resilience, tensile strength, abrasion and a wide range of chemical resistance. RS-400 rubber comes with buff back, cloth profile or bonding layer for easy application.

SPECIFICATIONS

| PHYSICAL PROPERTIES | VALUES |
|------------------------------------|---|
| Density (gr/cc) | .98 lb/ft ³ (.98 g/cm ³) |
| Durometer (Shore A) | 38+/-5 |
| Tensile (min) kg / cm ² | 3415 PSI (240 kg/cm ²) |
| Elongation (%) | 810% |
| Tear (kg/cm – min.) | 224 lbs/inch (15.74 kg/cm) |
| Abrasion Resistance | 80 mm ³ |
| Compression 70°C 24 hrs | 15% |
| Temperature Range | -40°F to 158°F (-40°C to 70°C) |

ADHESIVE SYSTEM

| COAT | ADHESIVE |
|-------------------|-------------|
| 1st Coat (Primer) | Chemlok 205 |
| 2nd Coat Metal | RS-2000 |
| 3rd Coat Metal | RS-2000 |
| 4th Coat Rubber | RS-2000 |

STANDARD ROLL SIZE

| GAUGE | WIDTH | LENGTH | AREA |
|------------|-------|--------|---------------------|
| 3mm - 50mm | 1.21m | 9.14m | 11.14m ² |
| 1/8" - 2" | 48" | 30' | 120ft ² |



APPLICATIONS

- Cyclones
- Separators
- Classifiers
- Vessels
- Chutes
- Pipe Linings
- Skirting

BENEFITS

- Abrasion Resistant
- High resilience
- Reduces corrosion
- Vibration & noise absorbing

APPLICATION NOTES:

1. Use application procedure for guidance.
2. Observe adhesive drying time specifications.
3. Storage: Store in cool and dry area.
4. For best adhesion rubber to rubber use Rubber Primer before RS-2000.
5. Contact your account representative for more information.

Disclaimer: The above guidelines are based on general industry practices and not applicable to all installations. Application methods should comply with RubberSource application instructions. The data values use is an approximate value and may vary based on individual application methodology and local atmospheric conditions.