

**RS-B4CN Pre Cured Black Bromobutyl Blend** made from bromobutyl/Natural Blend polymers. It combines the properties of good heat resistance, diffusion resistance to gases such as nitrogen oxides, sulfur dioxide, and saturated water vapors. It also has very good resistance to corrosive acids, mineral, bases, aqueous phases, polar solvents and alkalis, while still retaining a moderate abrasion resistance. It has excellent resistance to ozone and outdoor weathering effects, and suitable for use with a range of chemicals including oxygenated solvents and hydraulic fluid. Suitable for most applications where high acid, chemical or temperature resistance is required. Available with a bonding layer.

## SPECIFICATIONS

PHYSICAL PROPERTIES	VALUES
Durometer (ASTM D2240)	55 +/- 5 (Shore A)
Tensile (min) kg / cm <sup>2</sup>	570 PSI (40 kg/cm <sup>2</sup> )
Elongation (%)	370%
Tear (kg/cm – min.)	85 lbs/inch (15kg/cm)
Abrasion Resistance	320 mm <sup>3</sup>
Specific Gravity	1.25
Temperature (Operating)	185°F to 85°C

## RESISTANCE TO

MATERIAL	VALUE
Abrasion, Sliding	Good
Abrasion, Impingement	Fair
Acid (Diluted)	Excellent
Acid (Concentrated)	Excellent
Salt Solutions	Excellent
Oxygenated Solvents	Good
Animal & Vegetable Oils	Poor
Oil & Gasoline	Poor

## ATMOSPHERIC AGING

MATERIAL	VALUE
Low Temperature Flexibility	Good
Moisture Resistance	Good
Compression Set	Good
Permeability	Good

## ADHESIVE SYSTEM

COAT	ADHESIVE
1st Coat (Primer)	Chemlok 205
2nd Coat Metal	RS-2000
3rd Coat Metal	RS-2000
4th Coat Rubber	RS-2000

## STANDARD ROLL SIZE

GAUGE	WIDTH	LENGTH	AREA
3mm - 50mm	1.21m	9.14m	11.14m <sup>2</sup>
1/8" - 2"	48"	30'	120ft <sup>2</sup>

## APPLICATION NOTES:

1. Use application procedure for guidance.
2. Observe adhesive drying time specifications.
3. Storage: Store in cool and dry area.
4. For best adhesion rubber to rubber use Rubber Primer before RS-2000.
5. Contact your account representative for more information.

## APPLICATIONS

- Classifiers
- Vessels
- Pickle Lines
- Flue gas desulfurisation (FGD)
- Rail and OTR tankers
- Ship cargo hold

## BENEFITS

- Abrasion Resistant
- High resilience
- Reduces corrosion

Disclaimer: The above guidelines are based on general industry practices and not applicable to all installations. Application methods should comply with RubberSource application instructions. The data values use is an approximate value and may vary based on individual application methodology and local atmospheric conditions.