

RS-B60FG Pre Cured Black Bromobutyl FDA Compliant, made from bromobutyl polymer. It combines the properties of good heat resistance, and very good resistance to corrosive acids and alkalis, while still retaining a moderate abrasion resistance. It has excellent resistance to ozone and outdoor weathering effects, and suitable for use with a range of chemicals including oxygenated solvents and hydraulic fluid. Suitable for most applications where high acid, chemical or temperature resistance is required. Excellent for water treatment applications. Available with a bonding layer. FDA compliant as per 21CFR177.2600.

SPECIFICATIONS

PHYSICAL PROPERTIES	VALUES
Durometer (Shore A)	60 +/-5
Tensile	1280 PSI (90 kg/cm ²)
Elongation	350%
Tear	165 lbs/inch (161.3 kg/cm)
Abrasion Resistance	80 mm ³
Temperature Range	-40°F to 260°F (-40°C to 127°C)
Specific Gravity	1.20

RESISTANCE TO

MATERIAL	VALUE
Abrasion, Sliding	Good
Abrasion, Impingement	Fair
Acid (Diluted)	Excellent
Acid (Concentrated)	Excellent
Salt Solutions	Excellent
Oxygenated Solvents	Good
Animal & Vegetable Oils	Good
Oil & Gasoline	Poor

ATMOSPHERIC AGING

MATERIAL	VALUE
Low Temperature Flexibility	Good
Moisture Resistance	Good
Compression Set	Good
Permeability	Good

ADHESIVE SYSTEM

COAT	ADHESIVE
1st Coat (Primer)	Chemlok 205
2nd Coat Metal	RS-2000
3rd Coat Metal	RS-2000
4th Coat Rubber	RS-2000

STANDARD ROLL SIZE

GAUGE	WIDTH	LENGTH	AREA
3mm - 50mm	1.21m	9.14m	11.14m ²
1/8" - 2"	48"	30'	120ft ²

APPLICATION NOTES:

1. Use application procedure for guidance.
2. Observe adhesive drying time specifications.
3. Storage: Store in cool and dry area.
4. Contact your account representative for more information.

APPLICATIONS

- Classifiers
- Vessels
- Water Treatment

BENEFITS

- Abrasion Resistant
- High resilience
- Reduces corrosion
- FDA Compliant

Disclaimer: The above guidelines are based on general industry practices and not applicable to all installations. Application methods should comply with RubberSource application instructions. The data values use is an approximate value and may vary based on individual application methodology and local atmospheric conditions.